

Brush 60[®] Strip

Materion Brush Performance Alloys' Brush 60 is a high performance, lower priced copper beryllium alloy offering cost effective solutions for many applications. Available in mill hardened tempers, Brush 60 was performance engineered for electronic contact and spring applications in the computer, datacom and telecommunications markets.

As components are reduced in size and signal requirements become more stringent, the selection of materials is of increasing importance. Total cost solutions demand materials which provide design flexibility, ease of manufacturing, and life cycle reliability. Brush 60 (C17460) was performance engineered with these criteria in mind. Key benefits include:

- Greater contact force and conductivity to improve signal transfer
- Superior high temperature durability
- Freedom to form intricate parts at high strength levels
- Complete recyclability

CHEMICAL COMPOSITION (weight percent)

Beryllium (Be)	Nickel (Ni)	Zirconium (Zr)	Tin (Sn)	Copper
0.15 – 0.5	1.0 – 1.4	0.5 max	0.25 max.	Balance

PHYSICAL PROPERTIES

Elastic Modulus	Density	Electrical Conductivity	Thermal Conductivity	Coefficient of Thermal Expansion
19,600 ksi 135 GPa	0.318 lb/in ³ 8.81 g/cm ³	50% IACS (nominal) 2.9 μ-ohm-cm (nominal)	128 BTU/hr·ft ·°F 225 W/m·K	9.8 x 10 ⁻⁶ in/in·°F 17.5 x 10 ⁻⁶ mm/mm·°C

TYPICAL MECHANICAL PROPERTIES

Temper	0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation (Minimum)	Formability (R/t) For a 90 Degree Bend	
	(ksi)	(MPa)	(ksi)	(MPa)		Good Way	Bad Way
¾ HT	95 – 115	655 – 795	115 – 135	795 – 930	11%	0.7	0.7
HT	105 – 125	720 – 860	120 – 140	825 – 965	10%	1.5	1.5

Note: A "good way" bend has its axis perpendicular to the rolling direction of the strip. Strip less than 0.010" (0.25 mm) may form somewhat better. Please see formability vs. thickness charts on reverse side

STANDARD AVAILABILITY



Brush 60 strip is available in widths ranging from 0.050" to 16" (1.27 mm to 452.7 mm) and in thicknesses ranging from 0.002" to 0.080" (0.05 mm to 2.03 mm).

SPECIFICATIONS

UNS C17460

RELATED INFORMATION

Additional information on Brush Alloy 310 can be obtained by calling 800-375-4205.



SAFE HANDLING OF COPPER BERYLLIUM

Handling copper beryllium in solid form poses no special health risk. Like many industrial materials, beryllium-containing materials may pose a health risk if recommended safe handling practices are not followed. Inhalation of airborne beryllium may cause a serious lung disorder in susceptible individuals. The Occupational Safety and Health Administration (OSHA) has set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Material Safety Data Sheet (MSDS) before working with this material. For additional information on safe handling practices or technical data on copper beryllium, contact Materion Brush Performance Alloys, Technical Service Department at 1-800-375-4205.

CHINA/HONG KONG

TEL: + (852) 2318-1960 / 1907
brushalloysHK-info@materion.com

INDIA/PUNE

TEL: + (91) 99606-33744
brushalloysIN-info@materion.com

SINGAPORE/ASEAN

TEL: + (65) 6842-4456
brushalloysSG-info@materion.com

CHINA/SHANGHAI

TEL: + (86) 21-5237-2328
brushalloysCN-info@materion.com

JAPAN

TEL: + (81) 33 230 2961
brushalloysJP-info@materion.com

TAIWAN, R.O.C.

TEL: + (886) 2-2747-8800 x-121
brushalloysTW-info@materion.com

GERMANY

TEL: + (49) 711-830-930
brushalloysDE-info@materion.com

REPUBLIC OF KOREA

TEL: + (82) 32-811-2171
brushalloysKR-info@materion.com

UNITED KINGDOM & IRELAND

TEL: + (44) 118-930-3733
brushalloysUK-info@materion.com